

Papel 100% reciclado para bolsas
de supermercados y comercio electrónico.

Características técnicas

TEST	NORMA	UNIDAD	AiaBag GreenKraft									
Gramaje	EN ISO 536	gr/m²	50	75	80	85	90	100	110	120	125	+~3%
Humedad	EN ISO 287	%	8	8	8	8	8	8	8	8	8	+~1
COBB 60	EN ISO 535	gr/m2	30	30	30	30	30	30	30	30	30	+~5%
Resistencia al estallido	EN ISO 2758	Kpa m²/g	2.6	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	Indicativo
Alargamiento SM	EN ISO 1924 / 2	%	1.4	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	-10%
Alargamiento ST	EN ISO 1924 / 2	%	2.1	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	-10%
Long. Rotura SM	EN ISO 1924 / 2	m	8000	6500	6500	6800	6800	7000	7000	7000	7000	-10%
Long. Rotura ST	EN ISO 1924 / 2	m	2800	2300	2300	2600	2600	2800	2800	2800	2800	-10%
Porosidad	EN ISO 5636-5	S	35	60	60	60	60	60	60	60	60	Indicativo
SCT	EN ISO 9895	kn/m	-	1.43	1.52	1.62	1.71	1.90	2.10	2.40	2.50	-10%

