

Paper for bags, 100% recycled.
Commercial use, both Retail and Take away.

Technical characteristics

| TEST | STANDARD | DIMENSION | AiaBag Plus | | | | | | | | | | | |
|--------------------------------|-----------------|-----------------------|-------------|------|------|------|------|------|------|------|------|------|------|------------|
| Nominal basic weight | EN ISO 536 | gr/m ² | 70 | 75 | 80 | 85 | 90 | 95 | 100 | 110 | 115 | 120 | 125 | +/-3% |
| Nominal moisture | EN ISO 287 | % | 8 | 8 | 8 | 8 | 8 | 8 | 8 | 8 | 8 | 8 | 8 | +/-1 |
| COBB 60 | EN ISO 535 | gr/m ² | 40 | 40 | 40 | 40 | 40 | 40 | 40 | 40 | 40 | 40 | 40 | Max.50 |
| Bursting Strength | EN ISO 2758 | Kpa m ² /g | 2.2 | 2.2 | 2.2 | 2.2 | 2.2 | 2.2 | 2.2 | 2.2 | 2.2 | 2.2 | 2.2 | Indicative |
| Stretch MD | EN ISO 1924 / 2 | % | 1.6 | 1.6 | 1.6 | 1.6 | 1.6 | 1.6 | 1.6 | 1.6 | 1.6 | 1.6 | 1.6 | -10% |
| Stretch CD | EN ISO 1924 / 2 | % | 3.5 | 3.5 | 3.5 | 3.5 | 3.5 | 3.5 | 3.5 | 3.5 | 3.5 | 3.5 | 3.5 | -10% |
| Length strength MD | EN ISO 1924 / 2 | m | 6500 | 6500 | 6500 | 6500 | 6500 | 6500 | 6500 | 6500 | 6500 | 6500 | 6500 | -10% |
| Length strength CD | EN ISO 1924 / 2 | m | 2800 | 2800 | 2800 | 2800 | 2800 | 2800 | 2800 | 2800 | 2800 | 2800 | 2800 | -10% |
| Air resistance (Gurley) | EN ISO 5636-5 | S | 35 | 35 | 35 | 35 | 35 | 35 | 35 | 35 | 35 | 35 | 35 | Indicative |

