

Papel 100% reciclado para bolsas de supermercados y comercio electrónico.

## Características técnicas

TEST	NORMA	UNIDAD	AiaBag GreenKraft																
			40	45	50	55	60	65	70	75	80	85	90	95	100	110	120	125	
<b>Gramaje</b>	EN ISO 536	gr/m <sup>2</sup>	40	45	50	55	60	65	70	75	80	85	90	95	100	110	120	125	+/-3%
<b>Humedad</b>	EN ISO 287	%	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	+/-1
<b>COBB 60</b>	EN ISO 535	gr/m <sup>2</sup>	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	+/-5%
<b>Resistencia al estallido</b>	EN ISO 2758	Kpa m <sup>2</sup> /g	2.1	2,1	2,1	2,1	2,1	2,1	2.6	2.6	2.6	2.6	2.6	2.6	2.7	2.7	2.7	2.7	Indicativo
<b>Desgarro L</b>	EN ISO 1974	mN	240	245	250	265	280	300	420	460	500	540	580	620	660	740	820	860	Indicativo
<b>Desgarro T</b>	EN ISO 1974	mN	275	300	325	350	375	400	450	490	530	570	610	650	690	770	850	890	-10%



La marca de la gestión forestal responsable