

CEPI code 52

Papel de altas prestaciones para doble uso, tanto como liner como Fluting

Características objetivo

TEST	NORMA	UNIDAD	AiaNature DUO														
Gramaje nominal	ISO 536	gr/m ²	70	75	80	85	90	95	100	110	115	120	125	130	135	140	150
Humedad nominal	ISO 287	%	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8
SCT, DT	ISO 9895	Kn/m	1,1	1,2	1,4	1,45	1,6	1,7	1,8	2	2,1	2,2	2,3	2,4	2,5	2,6	2,8
COBB 60	EN ISO 535	gr/m ²	-	-	-	-	-	-	35	35	35	35	35	35	35	35	35
Resistencia al estallido	EN ISO 2758	Kpa	150	165	182	194	205	220	220	242	250	264	275	286	297	308	330
CMT 30/50 MD	EN ISO 7263	N	75	90	105	128	144	152	160	176	185	192	200	208	216	224	240

Características garantizadas

TEST	NORMA	UNIDAD	AiaNature DUO														
Gramaje nominal	ISO 536	gr/m ²	70	75	80	85	90	95	100	110	115	120	125	130	135	140	150
Variación		Nominal	+-3%	+-3%	+-3%	+-3%	+-3%	+-3%	+-3%	+-3%	+-3%	+-3%	+-3%	+-3%	+-3%	+-3%	+-3%
Humedad nominal	ISO 287	%	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8
Variación		Nominal	+-1	+-1	+-1	+-1	+-1	+-1	+-1	+-1	+-1	+-1	+-1	+-1	+-1	+-1	+-1
SCT	ISO 9895	Kn/m	1	1,1	1,2	1,35	1,4	1,5	1,6	1,8	1,9	2	2,1	2,2	2,3	2,4	2,6
COBB 60	EN ISO 535	gr/m ²	-	-	-	-	-	-	50	50	50	50	50	50	50	50	50
Resistencia al estallido	EN ISO 2758	Kpa	135	145	155	165	175	185	195	210	218	225	238	260	270	280	300
CMT 30/50 MD	EN ISO 7263	N	65	75	85	105	120	127	135	150	155	163	170	176	183	190	204

