

CEPI code 50

Liner ligero de varios gramajes con excelente maquinabilidad.

Características objetivo

TEST	NORMA	UNIDAD	AiaNature TL4																	
Gramaje nominal	ISO 536	gr/m ²	60	65	70	75	80	85	90	95	100	105	110	115	120	125	130	135	140	150
Humedad nominal	ISO 287	%	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8
SCT	ISO 9895	Kn/m	0,7	0,8	0,9	1	1,1	1,2	1,3	1,35	1,4	1,45	1,5	1,6	1,7	1,8	1,9	2,0	2,1	2,2
Resistencia al estallido	EN ISO 2758	Kpa	90	100	110	120	130	140	150	160	170	180	190	210	220	230	240	250	260	280

Características garantizadas

TEST	NORMA	UNIDAD	AiaNature TL4																	
Gramaje nominal	ISO 536	gr/m ²	60	65	70	75	80	85	90	95	100	105	110	115	120	125	130	135	140	150
Variación		Nominal	+3%	+3%	+3%	+3%	+3%	+3%	+3%	+3%	+3%	+3%	+3%	+3%	+3%	+3%	+3%	+3%	+3%	+3%
Humedad nominal	ISO 287	%	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8
Variación		Nominal	+1	+1	+1	+1	+1	+1	+1	+1	+1	+1	+1	+1	+1	+1	+1	+1	+1	+1
SCT	ISO 9895	Kn/m	0,5	0,6	0,7	0,8	0,9	1	1,1	1,15	1,2	1,25	1,3	1,4	1,5	1,6	1,7	1,8	1,9	2,0
Resistencia al estallido	EN ISO 2758	Kpa	75	85	95	105	115	130	140	150	160	170	180	200	210	220	230	240	250	270

