

CEPI code 50

Light liner produced in wide variety of grammages with excellent runnability.

Typical Value

TEST	STANDARD	DIMENSION	AiaNature TL																	
Basis Weight	ISO 536	gr/m ²	60	65	70	75	80	85	90	95	100	105	110	115	120	125	130	135	140	150
Nominal Humidity	ISO 287	%	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8
SCT	ISO 9895	Kn/m	0,7	0,8	0,9	1	1,1	1,2	1,3	1,35	1,4	1,45	1,5	1,6	1,7	1,8	1,9	2,0	2,1	2,2
Bursting Strength	EN ISO 2758	Kpa	90	100	110	120	130	140	150	160	170	180	190	210	220	230	240	250	260	280

Guaranteed Value

TEST	STANDARD	DIMENSION	AiaNature TL																	
Basis Weight	ISO 536	gr/m ²	60	65	70	75	80	85	90	95	100	105	110	115	120	125	130	135	140	150
Variation		Nominal	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%
Nominal Humidity	ISO 287	%	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8
Variation		Nominal	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1
SCT	ISO 9895	Kn/m	0,5	0,6	0,7	0,8	0,9	1	1,1	1,15	1,2	1,25	1,3	1,4	1,5	1,6	1,7	1,8	1,9	2
Bursting Strength	EN ISO 2758	Kpa	75	85	95	105	115	130	140	150	160	170	180	200	210	220	230	240	250	270

