

CEPI code 60 $\leq 100\text{g/m}^2$

CEPI code 41 $> 100\text{g/m}^2$

Light fluting with wide variety of grammages, excellent runnability and maximum performance and speed in corrugators.

Typical Value

TEST	STANDARD	DIMENSION	AiaNature FLUTE															
Basis Weight	ISO 536	gr/m ²	65	70	75	80	85	90	95	100	110	115	120	125	130	135	140	150
Nominal Humidity	ISO 287	%	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8
SCT	ISO 9895	Kn/m	0,9	1	1,1	1,2	1,3	1,4	1,5	1,6	1,65	1,7	1,8	1,9	2	2,1	2,2	2,3
CMT 30/50 MD	EN ISO 7263	N	-	-	85	90	115	130	135	140	145	155	160	170	180	190	200	220

Guaranteed Value

TEST	STANDARD	DIMENSION	AiaNature FLUTE															
Basis Weight	ISO 536	gr/m ²	65	70	75	80	85	90	95	100	110	115	120	125	130	135	140	150
Variation		Nominal	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%
Nominal Humidity	ISO 287	%	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8	8
Variation		Nominal	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1
SCT	ISO 9895	Kn/m	0,76	0,8	1	1,1	1,2	1,3	1,4	1,5	1,55	1,6	1,7	1,8	1,9	2	2,1	2,2
CMT 30/50 MD	EN ISO 7263	N	-	-	65	75	95	110	115	120	125	135	140	150	160	170	180	200

