

Papel para bolsas, 100% reciclado.

Características técnicas

TEST	NORMA	UNIDAD	AiaBag											
			70	75	80	85	90	95	100	110	115	120	125	
Gramaje	EN ISO 536	gr/m ²	70	75	80	85	90	95	100	110	115	120	125	+/-3%
Humedad	EN ISO 287	%	8	8	8	8	8	8	8	8	8	8	8	+/-1
Resistencia al estallido	EN ISO 2758	Kpa m ² /g	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	Indicativo
Alargamiento SM	EN ISO 1924 / 2	%	1.4	1.4	1.4	1.4	1.4	1.4	1.4	1.4	1.4	1.4	1.4	-10%
Alargamiento ST	EN ISO 1924 / 2	%	3	3	3	3	3	3	3	3	3	3	3	-10%
Long. Rotura SM	EN ISO 1924 / 2	m	6200	6200	6200	6200	6200	6200	6200	6200	6200	6200	6200	-10%
Long. Rotura ST	EN ISO 1924 / 2	m	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	-10%
Porosidad	EN ISO 5636-5	S	35	35	35	35	35	35	35	35	35	35	35	Indicativo

