

CEPI code 44

Semi-chemical fluting paper with high performance and excellent behaviour.

Typical value

TEST	STANDARD	DIMENSION	AiaNature SQ									
Basis Weight	ISO 536	gr/m ²	100	105	110	115	120	125	130	135	140	150
Nominal Humidity	ISO 287	%	9	9	9	9	9	9	9	9	9	9
SCT	ISO 9895	Kn/m	2,1	2,2	2,3	2,4	2,6	2,7	2,8	2,9	3,0	3,1
CMT	EN ISO 7263	N	200	210	220	230	264	274	286	297	308	330

Guaranteed Value

TEST	STANDARD	DIMENSION	AiaNature SQ									
Basis Weight	ISO 536	gr/m ²	100	105	110	115	120	125	130	135	140	150
Variation		Nominal	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%	+/-3%
Nominal Humidity	ISO 287	%	9	9	9	9	9	9	9	9	9	9
Variation		Nominal	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1	+/-1
SCT	ISO 9895	Kn/m	1,9	2	2,1	2,2	2,4	2,5	2,6	2,7	2,8	2,9
CMT 30/50 MD	EN ISO 7263	N	165	175	187	195	228	237	247	257	266	285

