

- o 100% recycled paper with 68 whiteness
- o Optimun quality
- o High performance for perfect copies
- o Suitable for photocopying, laser printing, ink-jet and faxing

TEST	STANDARD	DIMENSION	AiaPrintCopy		
Basis weight	ISO 536	g/m2	60	70	80
Thickness	ISO 534	um	75	85	100
Smoothness Bekk	ISO 5627	S	9,5	9,5	9,5
Whiteness	ISO 2470	%	68	68	68
Opacity	ISO 2471	%	>91	>94	>94
Tensile Strength MD	ISO 1924	kN/m	3,0	3,5	4,5
Tensile Strength CD	ISO 1924	kN/m	1,10	1,25	1,45

