

CEPI code 50

Light liner produced in wide variety of grammages with excellent runnability.

Typical Value

TEST	STANDARD	DIMENSION	AiaNature TL4										
Basis Weight	ISO 536	gr/m ²	75	80	85	90	95	100	105	110	115	120	125
Nominal Humidity	ISO 287	%	8	8	8	8	8	8	8	8	8	8	8
SCT	ISO 9895	Kn/m	1	1,1	1,2	1,3	1,35	1,4	1,45	1,5	1,6	1,7	1,8
		kn.m/kg	12,7	13	13,3	13,4	13,5	13,7	13,8	13,85	13,9	14,2	14,4
Bursting Strength	EN ISO 2758	Kpa	120	130	140	150	160	180	180	190	210	220	230
		Kpa.m ² /g	1,6	1,63	1,65	1,67	1,72	1,8	1,72	1,78	1,82	1,83	1,84

Guaranteed Value

TEST	STANDARD	DIMENSION	AiaNature TL4										
Basis Weight	ISO 536	gr/m ²	75	80	85	90	95	100	105	110	115	120	125
		Variation	Nominal	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%
Nominal Humidity	ISO 287	%	8	8	8	8	8	8	8	8	8	8	8
		Variation	Nominal	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1	+ -1
SCT	ISO 9895	Kn/m	0,8	0,9	1	1,1	1,15	1,2	1,25	1,3	1,4	1,5	1,6
		kn.m/kg	10,7	10,9	11	11,3	11,4	11,5	12	12,1	12,2	12,5	12,8
Bursting Strength	EN ISO 2758	Kpa	105	115	130	140	150	160	170	180	200	210	220
		Kpa.m ² /g	1,4	1,5	1,52	1,55	1,58	1,6	1,62	1,69	1,74	1,75	1,76

