

Papeles prensa de alta calidad 100% fibra reciclada, con excelente maquinabilidad y alta imprimibilidad.

L* a* b* Valores objetivo	L*	a*	b*
ISO 5631	81	-1	3

Valores objetivo

TEST	NORMA	UNIDAD	AiaPrint CS				
Gramaje	ISO 536	g/m ²	40	42	45	48.8	52
Blancura	ISO 2470-1 (C/2°)	%	57.5	57.5	57.5	57.5	57.5
Opacidad	ISO 2471	%	92	92	92	93	94
Mano	ISO 534	cm ³ /g	1.45	1.45	1.45	1.45	1.45
Lisura	PPS, ISO 8791	µm	4.1	4.1	4.1	4.1	4.1

