

CEPI code 44

Semi-chemical fluting paper with high performance and excellent behaviour.

Typical value

TEST	STANDARD	DIMENSION	AiaNature SQ					
Basis Weight	ISO 536	gr/m ²	100	105	110	115	120	125
Nominal Humidity	ISO 287	%	9	9	9	9	9	9
SCT	ISO 9895	Kn/m	2,1	2,2	2,3	2,4	2,6	2,7
		kn.m/kg	20	21	21	21	22	22
CMT	EN ISO 7263	N	200	210	220	230	264	274
		N.m ² /g	2	2	2	2	2,2	2,2

Guaranteed value

TEST	STANDARD	DIMENSION	AiaNature SQ					
Basis Weight	ISO 536	gr/m ²	100	105	110	115	120	125
		Variation	Nominal	+ -3%	+ -3%	+ -3%	+ -3%	+ -3%
Nominal Humidity	ISO 287	%	9	9	9	9	9	9
		Variation	Nominal	+ -1	+ -1	+ -1	+ -1	+ -1
SCT	ISO 9895	Kn/m	1,9	2	2,1	2,2	2,4	2,5
		kn.m/kg	18	18	19	19	20	20
CMT	EN ISO 7263	N	165	175	187	195	228	237
		N.m ² /g	1,5	1,6	1,7	1,8	1,9	1,9

