

Características técnicas

| TEST                     | NORMA           | UNIDAD   | AiaBag Plus |      |      |      |      |      |      |      |      |      |      |            |
|--------------------------|-----------------|----------|-------------|------|------|------|------|------|------|------|------|------|------|------------|
| Gramaje                  | EN ISO 536      | gr/m²    | 70          | 75   | 80   | 85   | 90   | 95   | 100  | 110  | 115  | 120  | 125  | + -3%      |
| Humedad                  | EN ISO 287      | %        | 8           | 8    | 8    | 8    | 8    | 8    | 8    | 8    | 8    | 8    | 8    | + -1       |
| COBB 60 C                | EN ISO 535      | gr/m2    | -           | -    | -    | -    | -    | -    | 40   | 40   | 40   | 40   | 40   | Max.50     |
| COBB 60 R                | EN ISO 535      | gr/m2    | -           | -    | -    | -    | -    | -    | 40   | 40   | 40   | 40   | 40   | Max.50     |
| Resistencia al estallido | EN ISO 2758     | Kpa m²/g | 2.2         | 2.2  | 2.2  | 2.2  | 2.2  | 2.2  | 2.2  | 2.2  | 2.2  | 2.2  | 2.2  | Indicativo |
| Alargamiento SM          | EN ISO 1924 / 2 | %        | 1.6         | 1.6  | 1.6  | 1.6  | 1.6  | 1.6  | 1.6  | 1.6  | 1.6  | 1.6  | 1.6  | -10%       |
| Alargamiento ST          | EN ISO 1924 / 2 | %        | 3.5         | 3.5  | 3.5  | 3.5  | 3.5  | 3.5  | 3.5  | 3.5  | 3.5  | 3.5  | 3.5  | -10%       |
| Long. Rotura SM          | EN ISO 1924 / 2 | m        | 6500        | 6500 | 6500 | 6500 | 6500 | 6500 | 6500 | 6500 | 6500 | 6500 | 6500 | -10%       |
| Long. Rotura ST          | EN ISO 1924 / 2 | m        | 2800        | 2800 | 2800 | 2800 | 2800 | 2800 | 2800 | 2800 | 2800 | 2800 | 2800 | -10%       |
| Porosidad                | EN ISO 5636-5   | S        | 35          | 35   | 35   | 35   | 35   | 35   | 35   | 35   | 35   | 35   | 35   | Indicativo |

