

Papel para bolsas, 100% reciclado.

Características técnicas

TEST	NORMA	UNIDAD	AiaBag HP				
Gramaje	EN ISO 536	gr/m²	110	115	120	125	+ -3%
Humedad	EN ISO 287	%	8	8	8	8	+ -1
COBB 60 C	EN ISO 535	gr/m2	40	40	40	40	Max.50
COBB 60 R	EN ISO 535	gr/m2	40	40	40	40	Max.50
Resistencia al estallido	EN ISO 2758	Kpa m²/g	2.3	2.3	2.3	2.3	Indicativo
Alargamiento SM	EN ISO 1924 / 2	%	1.6	1.6	1.6	1.7	-10%
Alargamiento ST	EN ISO 1924 / 2	%	3.5	3.5	3.5	3.5	-10%
Long. Rotura SM	EN ISO 1924 / 2	m	6600	6600	6600	6600	-10%
Long. Rotura ST	EN ISO 1924 / 2	m	2800	2800	2800	2800	-10%
Porosidad	EN ISO 5636-5	S	60	60	60	60	Indicativo

