

Papel para bolsas, 100% reciclado.
Uso comercial, tanto Retail como Take away.

Características técnicas

TEST	NORMA	UNIDAD	AiaBag Plus											
Gramaje	EN ISO 536	gr/m ²	70	75	80	85	90	95	100	110	115	120	125	+/-3%
Humedad	EN ISO 287	%	8	8	8	8	8	8	8	8	8	8	8	+/-1
COBB 60	EN ISO 535	gr/m ²	40	40	40	40	40	40	40	40	40	40	40	Max.50
Resistencia al estallido	EN ISO 2758	Kpa m ² /g	2.2	2.2	2.2	2.2	2.2	2.2	2.2	2.2	2.2	2.2	2.2	Indicativo
Alargamiento SM	EN ISO 1924 / 2	%	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	-10%
Alargamiento ST	EN ISO 1924 / 2	%	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	-10%
Long. Rotura SM	EN ISO 1924 / 2	m	6500	6500	6500	6500	6500	6500	6500	6500	6500	6500	6500	-10%
Long. Rotura ST	EN ISO 1924 / 2	m	2800	2800	2800	2800	2800	2800	2800	2800	2800	2800	2800	-10%
Porosidad	EN ISO 5636-5	S	35	35	35	35	35	35	35	35	35	35	35	Indicativo

